

# Strontium Titanate $\text{SrTiO}_3$

## Sputtering Targets



**Kurt J. Lesker**<sup>®</sup>  
Company

**MATERIALS**<sup>™</sup>  
DIVISION

### Applications

---

- Ferroelectric
- CMOS
- Thin film capacitor

### Features

---

- High purity
- Custom Sizes Available

### Process

---

- Manufacturing
  - Cold pressed
  - Sintered
  - Elastomer bonded to backing plate
- Cleaning and final packaging
  - Cleaned for use in vacuum
  - Protection from environmental contaminants
  - Protection during shipment

### Options

---

- 99.9% Minimum Purity
- Up to 12.0" Diameter Targets Available
- Planar Tiles Up to 8" X 5" for Larger Target Configurations

[www.lesker.com](http://www.lesker.com)

## Specifications

### Typical Analysis - 99.9% (3N) Purity

Metallic Impurities, ppm by weight

Al	Ba	Bi	Ca	Cl	Co	Cr	Fe	Hf	K
<5	<5	<5	<15	<15	<5	<5	<5	<20	<5

Mg	Mn	N	Na	Ni	Pb	S	Sb	Si	Sn
<5	<5	<50	<50	<5	<5	<5	<5	<5	<5

Theoretical Density	5.1 g/cc
Typical Density	3.66 g/cc
Sputter	RF
Max Power Density (Watts/Square Inch)	20
Appearance	White/Beige
Z Ratio	0.31
Particle Size	D50

Kurt J. Lesker Company (KJLC®) specifications and/or test data may not be copied, reproduced or referenced without express written permission of KJLC.

**Kurt J. Lesker**<sup>®</sup>  
Company Enabling Technology for a Better World | [www.lesker.com](http://www.lesker.com)

Kurt J. Lesker Company  
United States - [salesus@lesker.com](mailto:salesus@lesker.com)  
412.387.9200  
800.245.1656

Kurt J. Lesker Canada Inc.  
Canada - [salescan@lesker.com](mailto:salescan@lesker.com)  
416.588.2610  
800.465.2476

Kurt J. Lesker Company Ltd.  
EMEIA - [EMEIASales@lesker.com](mailto:EMEIASales@lesker.com)  
+44 (0) 1424 458100

Kurt.Lesker (Shanghai) Trading Company  
科特·莱思科(上海)商贸有限公司  
Asia - [salesasia@lesker.com](mailto:salesasia@lesker.com)  
+86 21 50115900